

# EPP SERIE (EUROPETPVC)

Designed for both Twist PET and PVC substrated  
Özellikle hem twist PET hem de PVC için kullanılmak üzere dizayn edilmiş solvent bazlı mürekkep  
**Printed Substrates** Twist Pet,PVC.

## ROTOGRAVUR

OVERPRINTING

EPP-XXXX

Standart Pigmentation

### TECHNICAL PROPERTIES

- According to the substrate heat resistance is between 140C-160C (3bar ,1 sn)
- Good ink transfer
- Does not contain TAA or Phtalate
- Production Viscosity:30-35 sn/D4/25 C

### PRINTING REQUIREMENTS

#### Printing Viscosity

- Rotogravure : 15-20 sn./D4/25 C

#### Printing Viscosity Preparations

- Rotogravure :50% Ethyl Alcohol-50% Ethyl Acetate mixture (1-1) or 100 % ethyl acetate

#### Drying Time Adjustments

- Accelerator :Ethyl Acetate Retarder :Ethoxy Propanol or Methoxy Propanol

### SHELF LIFE

- The shelf life of **EPP** series is 1 year in unopened packaging
- Shelf life of golds, imitation golds, silvers are 6 months in unopened packaging
- Shelf life of inks containing fanal pigments are 1 month.

**Not:**Yukarıdaki bilgiler laboratuvar test sonuçlarımıza dayanmaktadır.Uygulama şartlarındaki farklılıklar verileri değiştirebilir.Bu gibi durumlarda teknik departmanımıza başvurunuz.