



## **EOL-0001 Matt**

### **MATT OVERPRINT LACQUER**

**EOL-00001** is designed especially used for Twist PET substrate .It is used for rotogravure and flexo printing.

**Product Name:**Mat Overprint Lacquer

**Product Code:** EOL-0001 Matt

**Solid Content :**28+/-2

**Printing Type :**Rotogravure end flexo

**Production Viscosity :**25-30 sec (DIN CUP 4 , 25 C)

**Printing Viscosity :** **Rotogravure** :14-15 sn(DIN CUP 4, 25 C)

**Flekso** : 20-22 sec (DIN CUP 4 , 25 C)

**Thinner:** **Rotogravure** :50%Ethyl Acetate 50% Ethyl Alcohol

**Flekso** : 20%Ethyl Acetate 80% Ethyl Alcohol

**Application Amount:** 1-2 gr/m<sup>2</sup>

**Usage Area:** It is specially designed to be used in flat printing jobs where mattness is required. It also provides friction resistance to the printed surface.

**Shelf Life :** EOL-00001 Matt Overprint Lacquer is kept in original airtight packages for 1 year.

**Note:** The above information is based on our laboratory test results. Differences in application conditions may change the data. In this case, please contact our technical department.

