



EOL-0006

HEAT RESISTANCE OVERPRINT LACQUER

EOL-0006 is heat resistance overprint lacquer designed for rotogravure and flexo printing

Product Name : Heat Resistance Overprint Lacquer

Product Code: EOL-0006

Solid Content :28+/-2

Printing Application :Rotogravure and flexo

Production Viscosity:20-25 sn (DIN CUP 4 25 C)

Printing Viscosity Rotogravure :14-15 sec (DIN CUP 4 25 C)

Flexo : 20-22 sec(DIN CUP 4 25 C)

Thinner: Rotogravure :50%Ethyl Acetate 50% Ethyl Alcohol

Flexo : 20%Ethyl Acetate 80% Ethyl Alcohol

Application Amount: 1-2 gr/m²

Usage Area: It is specially designed for use in surface printing jobs where high heat resistance is required. It also provides friction resistance and gloss to the printed surface..

Shelf Life : EOL-0006 Heat Resistant Overprint Lacquer is kept in airtight original packages for 1 year.

Note: The above information is based on our laboratory test results. Differences in application conditions may change the data. In this case, please contact our technical department.