



## LH-9030

### AL FOIL/PVC AL FOIL/PS HEAT SEAL LACQUER

**LH-9030** is a heat seal lacquer suitable for rotogravure printing .

**Product Name:** Al Foil /PVC -Al Foil/PS Heat Seal lacquer

**Product Code:**LH-9030

**Solid Content:**25+/-2

**Printing Type:**Rotogravure

**Substrate :** Al Foil

**Production Viscosity:** 30-35 sec (DIN CUP 4 25 C)

**Printing Viscosity :** 16-18 sec (DIN CUP 4 25 C)

**Thinner:** Ethyl Acetate or MEK

**Application Amount:** 3-4 gr/m<sup>2</sup>

**Heat Seal Temperature:** 180 C

**Usage Area:** 3%-4% gr/m<sup>2</sup> solid applied on blister foil to be sealed to tough PVC and PS at 180 C.

**Shelf Life :** LH-9030 Heat Seal Lacquer is kept in original airtight packages for 1 year.

**Note:** The above information is based on our laboratory test results. Differences in application conditions may change the data. In this case, please contact our technical department.