



LO-5052

MOISTURE RESISTANCE OVERPRINT LACQUER

LO-5052 is moisture resistance overprint lacquer suitable for flexo and rotogravure printing.

Product Name :Moisture Resistance Overprint Lacquer

Product Code:LO-5052

Solid content :25+/-2

Printing Type :Rotogravure and flexo

Production Viscosity :25-30 sec (DIN CUP 4 25 C)

Printing Viscosity : **Rotogravure :**16-18 sec (DIN CUP 4 25 C)

Flexo: 21-25 sec (DIN CUP 4 25 C)

Thinner : **Rotogravure :**50% Ethyl Acetate 50% Ethyl Alcohol

Flexo : 20% Ethyl Acetate 80% Ethyl Acetate

Application Amount : 1-2 gr/m²

Usage Area : It is specially designed to be used in flat printing jobs requiring high moisture resistance. It also provides friction resistance and gloss to the printed surface.

Shelf Life : LO-5052 Moisture Resistant Top Coat is kept in airtight original packages for 1 year.

Note: The above information is based on our laboratory test results. Differences in application conditions may change the data. In this case, please contact our technical department.