



LO-5057

MOISTURE RESISTANT OVERPRINT LACQUER

LO-5057 is moisture resistance overprint lacquer suitable for flexo and rotogravure printing.

Product Name:Moisture resistance overprint lacquer

Product Code:LO-5057

Solid Content:28+/-2

Printing Type :Rotogravure and flexo

Production Viscosity:25-30 sec (DIN CUP 4 25 C)

Printing Viscosity: Rotogravure :16-18 sec (DIN CUP 4 25 C)

Flexo : 21-25 sec (DIN CUP 4 25 C)

Thinner: Rotogravure :50%Ethyl Acetate 50% Ethyl Alcohol

Flexo : 20% Ethyl Acetate 80% Ethyl Alcohol

Application Amount: 1-2 gr/m²

Usage Area : It is specially designed to be used in flat printing jobs requiring high moisture resistance. It also provides friction resistance and gloss to the printed surface.

Shelf Life : LO-5057 Moisture Resistant Overprint Lacquer is kept in original airtight packages for 1 year.

Note: The above information is based on our laboratory test results. Differences in application conditions may change the data. In this case, please contact our technical department.